

TECHNICAL DATA SHEET

KYNAR® HSV 900 POWDER

FLUORINATED HOMOPOLYMER POWDER

Kynar® HSV900 is a high molecular mass homopolymer of vinylidene fluoride, principally used as cathode and edge coating binder in Lithium-ion battery cells.

TYPE

PVDF

MAIN APPLICATIONS

- Automotive - BIW

DELIVERY FORM

- Powder

RHEOLOGICAL PROPERTIES

PROPERTIES	VALUE	UNIT	TEST STANDARD
Melt viscosity, 230°C (446°F) at 100 s-1	50	kPo	ASTM D3835
Solution viscosity	510	cPo	

THERMAL PROPERTIES

PROPERTIES	VALUE	UNIT	TEST STANDARD
Melting temperature, 10°C/min	165	°C	ASTM D3418

OTHER PROPERTIES

PROPERTIES	VALUE	UNIT	TEST STANDARD
Particle Size Distribution (PSD), Medium size particles (D50)	10	µm	GB/T 19077
Moisture absorption	< 0.1	%	GB/T 6283
Metal content, Metals (Cr, Mn, Fe, Co, Ni, Cu, Zn)	< 5 each	ppm	Internal Arkema
Density, 23°C (73°F)	1.77 - 1.79	g/cm³	ISO 1183-1

PACKAGING

- Available packaging:
- 20 kg / 44 lb boxes

Headquarters: Arkema France
51, Esplanade du Général de Gaulle
92800 Puteaux – France
T +33 (0)1 49 00 80 80