



Biodegradable Polymers

Product Information

Version 1.0

January 2013

G-PMS/B

ecoflex® F Blend C1200

Biodegradable polyester for compostable film

® = ecoflex is a registered trademarks of BASF SE;
Lupolen is a registered trademark of
Lyondell Basell group companies

Product description

ecoflex® F Blend C1200 is our biodegradable, statistical, aliphatic-aromatic copolyester based on the monomers 1,4-butanediol, adipic acid and terephthalic acid in the polymer chain. ecoflex® F Blend C1200 will biodegrade to the basic monomers 1,4-butanediol, adipic acid and terephthalic acid and eventually to carbon dioxide, water and biomass when metabolized in the soil or compost under standard conditions.

ecoflex® F Blend C1200 has properties similar to PE-LD because of its high molecular weight and its long chain branched molecular structure.



The Chemical Company

- Transparent to translucent, semi-crystalline structure with DSC melting point in the range of PE-LD: 110 - 120 °C
- High ultimate elongation at break and high failure energy (dart drop)
- High, but controllable water vapour transmission rate (WVTR)
- MVR (190 °C, 2.16 kg): 2.5 - 4.5 ml/10 min
- Good thermostability up to 230 °C
- regular predrying of pellets
- Good processability on blown film lines
- Down gaging to 10 µm possible
- Weldable and printable

ecoflex® F Blend C1200 fulfils the requirements of the European standard DIN EN 13432, the US standard ASTM D 6400 and the Japanese GreenPla standard for compostable and biodegradable polymers, because it can be degraded by micro-organisms. The biodegradation process in soil depends on the specific environment (climate, soil quality, population of micro-organisms).

ecoflex® F Blend C1200 is one of the few biodegradable plastics, which complies in its composition with the European and American food stuff legislation for food contact: EU Directive 2002/72/EC (as amended) and US food contact notification FCN 907. Specific limitations and more details are given on request. The converter or packer has to check the suitability of the article for the application.

Form supplied and storage

ecoflex® F Blend C1200 is supplied as lens shaped pellets in 1 t big bags or bulk containers. Temperatures during transportation and storage may not exceed 70 °C at any time. Storage time of unopened bags may not surpass 12 month at room temperature (23 °C).

Quality Control

ecoflex® F Blend C1200 is produced as a standard material in a continuous production process according to DIN EN ISO 9001:2000. The melt volume rate, MVR, at 190 °C, 2.16 kg, according to ISO 1133 has been defined as specified parameter for quality control. A certificate can be provided with each lot number (10 t) upon request. In order to obtain a high accuracy for the MVR measurement the granules should be dried for 30 minutes at 70 °C using e.g. an electronic moisture analyser (e.g. Brabender Aquatrac plus). Other data given in our literature are typical values, which are not part of our product specification for ecoflex® F Blend C1200.

Applications

ecoflex® F Blend C1200 has been developed for the conversion to flexible films using a blown film or cast film process. Typical applications are packaging films, agricultural films and compost bags. In view of numerous factors influencing functionality and shelf life of ecoflex® films and finished articles made thereof these parameters have to be tested by the converters before utilisation.

We supply technical service information concerning the blown or cast film process with ecoflex® F Blend C1200 on demand.

Intellectual Property

It is the responsibility of those to whom we supply our products to ensure that any proprietary rights and existing laws and legislation are observed. Some uses of ecoflex® and product obtained by use of ecoflex® are subject of intellectual property rights. Purchase of ecoflex® does not entitle the buyer or any third to produce, offer or use any blends of ecoflex® protected under property rights and all their equivalents as listed here:

- EP-B 1656423
- EP-B 937120
- EP-B 950689
- EP-B 1838784
- EP-B 947559
- EP-B 965615

Typical basic material properties of ecoflex® F Blend C1200

Property	Unit	Test Method	ecoflex® F Blend C1200	Lupolen® 2420 F
Mass density	g/cm ³	ISO 1183	1.25 - 1.27	0.924
Melt flow rate MFR 190°C, 2.16kg	g/10 min	ISO 1133	2.7 - 4.9	0.6 - 0.9
Melt volume rate MVR 190°C, 2.16kg	ml/10 min	ISO 1133	2.5 - 4.5	0.8 - 1.2
Melting point	°C	DSC	110 - 120	111
Shore D hardness	–	ISO 868	32	48
Vicat VST A/50	°C	ISO 306	91	96

Typical properties of ecoflex® F Blend C1200 blown film, 50 µm

Property	Unit	Test Method	ecoflex® F Blend C1200	Lupolen® 2420 F
Transparency	%	ASTM D 1003	82	89
Tensile strength	N/mm ²	ISO 527	35/44	26/20
Ultimate strength	N/mm ²	ISO 527	36/45	–
Ultimate Elongation	%	ISO 527	560/710	300/600
Failure Energy (Dyna Test)	J/mm	ISO 53373	24	5.5
Permeation rates:				
Oxygen (23°C, dry)	cm ³ /(m ² ·d·bar)	ASTM D 3985	1200	2900
Water vapour (23°C, 85% r.h.)	[g/(m ² ·d)]	ASTM F-1249	135	1.7

Note

The information submitted in this document is based on our current knowledge and experience. In view of the many factors that may affect processing and application, these data do not relieve processors of the responsibility of carrying out their own tests and experiments; neither do they imply any legally binding assurance for a special purpose. It is the responsibility of those to whom we supply our products to ensure that any proprietary rights and existing laws and legislation are observed.

For more information, contact us.

Shenzhen Chuangxin Plastic Technology Co., Ltd.

Tel: +86 18676057437 Email: xl1797110736@163.com

<https://www.cxinplas.com>