



# Teflon™ FEP CJ 99

## Molding and Extrusion Resin

### Product Information

For inventory control purposes, product name may be followed by an X.

Products labeled FEP CJ 99 and FEP CJ 99 X are equivalent, and all information in this document is applicable to both.

#### Typical Applications

Wire and cable insulation, small tubing, and injection molded parts.

#### Description

Teflon™ FEP CJ 99 is a melt-processible copolymer of tetrafluoroethylene and hexafluoropropylene, without additives, that meets the requirements of ASTM D 2116 Type I.

Thanks to the unique combination of a melt flow rate in the range of 9 g/10 min and MIT flex life above 40,000 cycles, this resin offers both attractive processing speeds and high stress-crack resistance in addition to the excellent characteristics typical of Teflon™ fluoroplastic resins, such as non-aging characteristics, chemical inertness, exceptional electrical properties, low flammability, heat resistance, toughness and flexibility, low coefficient of friction, non-stick characteristics, negligible moisture absorption, and excellent weather resistance. The increased transparency of Teflon™ FEP CJ 99 will also allow better colorability.

Stress crack resistance is an important element in establishing end-use performance. Extensive testing of wire and cable constructions is required for definitive performance evaluation. Well-known and most comprehensive tests for stress crack resistance of wire and cable are mandrel wrap tests as described in the military specification MIL-W-22759 (aerospace) and ISO 6722/LV112 (automotive). Experience has shown that the MIT folding endurance or flex life test, based on ASTM D 2176, performed on a thin film of resin, gives a good correlation with stress crack resistance. Resins with a higher MIT flex life perform better in the stress-crack resistance tests. Teflon™ FEP CJ 99 has a higher degree of stress crack resistance than most FEP resins with similar viscosity (MFR) and offers higher productivity than FEP resins with similar stress crack resistance (MIT). We recommend that for applications involving repeated thermal and flex cycling, specific tests on the final cable always should be undertaken. The MIT test results should be viewed as a guide to comparative performance of the various grades of resin.

#### Processing

Teflon™ FEP CJ 99 fluoroplastic resin can be processed by conventional melt extrusion, and by injection, compression, and blow molding processes. For smooth feeding to extrusion equipment, it is supplied in 3 mm (0.12 in) pellets. The extruders and molding machines used for Teflon™ FEP CJ 99 should be constructed of high nickel alloy corrosion-resistant materials and capable of operating at temperatures up to 400 °C (750 °F).

#### Safety Precautions

Industrial experience has proven that adequate ventilation, in properly maintained processing and handling areas, will eliminate known hazards to personnel. Resin containers should be opened and used in well-ventilated areas.

Equipment used to process at melt temperatures should be provided with local exhaust ventilation (LEV) to completely remove all fumes and vapors from the processing area. In addition, care should be exercised to avoid the contamination of cigarettes and other forms of smoking tobacco when using fluoroplastic resins. Before processing any fluoroplastics, read the Material Safety Data Sheet, available upon request from our Customer Service Group at (844) 773-CHEM/2436 in the U.S. or (302) 773-1000 outside of the U.S. Also read the detailed information in the latest edition of the "Guide to the Safe Handling of Fluoropolymer Resins," published by the Fluoropolymers Division of The Society of the Plastics Industry ([www.fluoropolymers.org](http://www.fluoropolymers.org)) or by PlasticsEurope ([www.plasticseurope.org](http://www.plasticseurope.org)).

#### Food Contact Compliance

Properly processed products made from Teflon™ FEP CJ 99 resin can qualify for use in contact with food in compliance with FDA 21 CFR 177.1550 and European Regulation (EU) No. 10/2011. For details and information, please contact your Chemours sales representative.

#### Storage and Handling

The properties of Teflon™ FEP CJ 99 resin are not affected by storage time. Ambient storage conditions should be designed to avoid airborne contamination and water condensation on the resin when opening and emptying the packaging.

#### Packaging

Teflon™ FEP CJ 99 is packaged in 25-kg, single layer, plastic bags. For convenient shipment, orders of 1,000-kg pallets are recommended.

**Table 1: Typical Property Data for Teflon® FEP CJ 99 Molding and Extrusion Resin**

Property	Test Method <sup>1</sup>		Unit	Typical Value
<b>GENERAL</b>				
Melt Flow Rate (MFR at 372 °C [702 °F]/5.0 kg)	ISO 12086	D 2116	g/10 min	9
Specific Gravity	ISO 1183	D 792		2.14
Critical Shear Rate (372 °C/702 °F)		Chemours	1/s	29
Guide DDR Range for Cable Extrusion				60-120
<b>MECHANICAL</b>				
Tensile Strength, 23 °C (73 °F)	ISO 12086	D 638	MPa (psi)	28 (4,060)
Elongation, 23 °C (73 °F)	ISO 12086	D 638	%	300
Hardness, Shore Durometer	ISO 868	D 2240		D 56
Impact Strength, Notched Izod, 23 °C (73 °F)	ISO 180	D 256	kJ/m <sup>2</sup>	No Break
MIT Folding Endurance (0.20 mm, 8 mil film)		D 2176 <sup>5</sup>	Cycles	40,000
<b>ELECTRICAL</b>				
Relative Permittivity, 1 kHz	IEC 250	D 150		2.03
Relative Permittivity, 1 GHz	IEC 250	D 150		2.03
Dissipation Factor, tg δ, 1 kHz	IEC 250	D 150		0.00005
Dissipation Factor, tg δ, 1 GHz	IEC 250	D 150		0.0008
Dielectric Strength, Short Time, 0.25 mm Film	IEC 243	D 149	kV/mm	> 100
<b>THERMAL</b>				
Melting Point		D 4591/D 3418	°C (°F)	255 (491)
Continuous Service Temperature <sup>2</sup>		—	°C (°F)	205 (400)
Flammability Classification <sup>3,4</sup>		UL 94		V-0
Limiting Oxygen Index	ISO 4589	D 2863	%	> 95
<b>OTHER</b>				
Chemical Resistance		D 543		Excellent
Water Absorption, 24 hr		D 570	%	< 0.01
Weather Resistance				Excellent

Note: Teflon® FEP CJ 99 meets the requirements of ASTM D 2116-07(2012), Type I.

Typical properties are not suitable for specification purposes.

<sup>1</sup> ASTM method unless otherwise specified.

<sup>2</sup> Definition of continuous service temperature: The continuous service temperature is based on accelerated heat-aging tests, and represents the temperature at which tensile strength and ultimate elongation retains 50% of the original values, after 20,000 hr thermal aging. When considering the use of Teflon® FEP CJ 99 at elevated temperatures, especially in combination with mechanical, electrical or chemical exposure, preliminary testing should be done to verify suitability.

<sup>3</sup> These results are based on laboratory tests, under controlled conditions, and do not reflect performance under actual fire conditions.

<sup>4</sup> Current rating is a typical theoretical value.

<sup>5</sup> Historical Standard.

### HOW TO USE THE TEFLON® BRAND NAME WITH YOUR PRODUCT

Teflon® is a registered trademark of Chemours for its brand of fluoroplastic resins, coatings, films, and dispersions. The Teflon® brand name is licensed by Chemours in association with approved applications. Without a trademark license, customers may not identify their product with the Teflon® brand name, as Chemours does not sell such offerings with the Teflon® trademark. Unlicensed customers may refer to the Chemours product offering with only the Chemours name and product code number descriptor as Chemours sells its product offerings. There are no fair use rights or exhaustion of rights to use the Teflon® trademark from buying from Chemours, a Chemours customer, or a distributor without a trademark license from Chemours.

If you are interested in applying for a trademark licensing agreement for the Teflon® brand, please visit [www.teflon.com/license](http://www.teflon.com/license)

**CAUTION:** Do not use or resell Chemours™ materials in medical applications involving implantation in the human body or contact with internal body fluids or tissues unless agreed to by Seller in a written agreement covering such use. For further information, please contact your Chemours representative. For medical emergencies, spills, or other critical situations, call (866) 595-1473 within the United States. For those outside of the United States, call (302) 773-2000.

The information set forth herein is furnished free of charge and based on technical data that Chemours believes to be reliable. It is intended for use by persons having technical skill, at their own discretion and risk. The handling precaution information contained herein is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Because conditions of product use are outside our control, Chemours makes no warranties, express or implied, and assumes no liability in connection with any use of this information. As with any material, evaluation of any compound under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate under or a recommendation to infringe any patents.

NO PART OF THIS MATERIAL MAY BE REPRODUCED, STORED IN A RETRIEVAL SYSTEM OR TRANSMITTED IN ANY FORM OR BY ANY MEANS ELECTRONIC, MECHANICAL, PHOTOCOPYING, RECORDING OR OTHERWISE WITHOUT THE PRIOR WRITTEN PERMISSION OF CHEMOURS.

**For more information, contact us.**

Shenzhen Chuangxin Plastic Technology Co., Ltd.

Tel : +86 18676057437 E-mail : xl1797110736@163.com

[https://www.cxinplas.com](http://www.cxinplas.com)