

Fluoropolymer

NEOFLON PFA AP-201SH

TECHNICAL DATASHEET

NEOFLON PFA AP-201SH is a highly flowable and fully fluorinated resin. It is suitable for injection molding of complicated shape products and extrusion molding of thin wall electric wire.

Introduction

- **AP-201SH** is a copolymer of tetrafluoroethylene and perfluoroalkylvinylether.
- High purity PFA with terminal groups fully fluorinated.
- **Good melt flowability** while maintaining excellent properties of PTFE. It can be melt-molded as a thermoplastic resin by **injection molding** and **extrusion molding**.
- Suitable for injection molding of **complicated shaped products** and extrusion molding of **thin-walled electric wires**. It is used for small parts of a semiconductor.
- **Less fluoride ions** due to the fluorinated terminal group.
- **Excellent chemical resistance** which is not affected by most of the chemicals.
- It retains flexibility without losing toughness under the environment from cryogenic to high temperature.
- **Low dielectric constant and dielectric loss tangent** in a wide range of temperature and frequency.
- It shows high electrical resistance and dielectric strength.
- **Nonflammable** like POLYFLON PTFE and NEOFLON FEP.
- **Excellent weather resistance**. No properties change even when exposed outside for a long time.
- Non-stickiness. It shows excellent releasability and water repellency / oil repellency.

General physical properties

Item	Unit	Value	Test Method
MFR	g/10min	28	ASTM D 3307 Compliant
Melting Point	°C	304	DSC
Specific Gravity	-	2.15	ASTM D 792 Compliant
Tensile Strength	MPa	32	ASTM D 1708 Compliant
Elongation	%	402	ASTM D 1708 Compliant

* The above values are representative values, not guaranteed values.

Handling method / Safety information

- Be sure to read the notes on SDS and labels before use.
- This product is intended for general industry, and therefore its adequacy and safety as a raw material for medical purposes cannot be guaranteed.

Packing specification

- 25Kg

For more information, contact us.

Shenzhen Chuangxin Plastic Technology Co., Ltd.

Tel: +86 18676057437 E-mail: xl1797110736@163.com

<https://www.cxinplas.com>