

## Fluoropolymer

# NEOFLON PFA AP-230AS

### TECHNICAL DATASHEET

**NEOFLON PFA AP-230AS is a conductive fluorocarbon resin.  
It is suitable for extrusion molding.**

#### Introduction

- **AP-230AS** is a copolymer of tetrafluoroethylene and perfluoroalkyl vinyl ether.
- It is a **PFA with conductivity**.
- **Good melt flowability** while maintaining excellent properties of PTFE. It can be melt-molded as a thermoplastic resin by **extrusion molding, transfer molding, compression molding** and the like.
- Especially, it is used for **thin-walled tubes for copy rolls** by extrusion molding.
- **Excellent chemical resistance** which is not affected by most of the chemicals.
- It can also be adopted to conductive **valve lining applications**.
- It retains flexibility without losing toughness under the environment from cryogenic to high temperature.
- No change in the resistance value up to 200 °C.
- Non-stickiness. It shows excellent releasability and water repellency / oil repellency.

#### General physical properties

Item	Unit	Value	Test Method
MFR	g/10min	1.9	ASTM D 3307 Compliant
Melting Point	°C	300	DSC
Volume resistivity	$\Omega \cdot \text{cm}$	$7.5 \times 10^{12}$	DAIKIN Method
Tensile Strength	MPa	35	ASTM D 1708 Compliant
Elongation	%	260	ASTM D 1708 Compliant

\* The above values are representative values, not guaranteed values.

#### Handling method / Safety information

- Be sure to read the notes on SDS and labels before use.
- This product is intended for general industry, and therefore its adequacy and safety as a raw material for medical purposes cannot be guaranteed.

#### Packing specification

- 50Kg

**For more information, contact us.**

**Shenzhen Chuangxin Plastic Technology Co., Ltd.**

**Tel: +86 18676057437 E-mail: [xl1797110736@163.com](mailto:xl1797110736@163.com)**

**<https://www.cxinplas.com>**